



MATERIAL SAFETY DATA SHEET

SikaLatex R

HMIS

HEALTH	1
FLAMMABILITY	1
REACTIVITY	0
PERSONAL PROTECTION	B

1. Product And Company Identification

Supplier

Sika Corporation
201 Polito Ave
Lyndhurst, NJ 07071

Company Contact: EHS Department
Telephone Number: 201-933-8800
FAX Number: 201-933-9379
Web Site: www.sikausa.com

Manufacturer

Sika Corporation
201 Polito Ave
Lyndhurst, NJ 07071

Company Contact: EHS Department
Telephone Number: 201-933-8800
FAX Number: 201-933-9379
Web Site: www.sikausa.com

Supplier Emergency Contacts & Phone Number

CHEMTREC: 800-424-9300
INTERNATIONAL: 703-527-3887

Manufacturer Emergency Contacts & Phone Number

CHEMTREC: 800-424-9300
INTERNATIONAL: 703-527-3887

Issue Date: 03/18/2004

Product Name: SikaLatex R
CAS Number: Not Established
Chemical Family: Butyl Acrylate/Styrene Copolymer Dispersion
MSDS Number: 3122
Product Code: 0132540

2. Composition/Information On Ingredients

Ingredient Name	CAS Number	Percent Of Total Weight
ACRYLIC POLYMER	Trade Secret	

3. Hazards Identification

Eye Hazards

May cause eye irritation.

Skin Hazards

May cause skin irritation.

Ingestion Hazards

May be harmful if swallowed.

Inhalation Hazards

May cause nose, throat, and lung irritation.

MATERIAL SAFETY DATA SHEET

SikaLatex R

4. First Aid Measures

Eye

In case of contact, hold eyelids apart and immediately flush eyes with plenty of tepid water for at least 15 minutes. Get medical attention immediately if irritation develops and persists.

Skin

In case of contact, immediately flush skin with soap and plenty of tepid water for at least 15 minutes. Get medical attention immediately if irritation (redness, rash, blistering) develops and persists.

Ingestion

If swallowed, induce vomiting immediately if directed to do so by medical personnel. If victim is fully conscious, give one or two cups of water or milk to drink.

Inhalation

Remove to fresh air. Get medical attention immediately.

5. Fire Fighting Measures

Flash Point: >200 °F

Autoignition Point: N/AV °F

Fire And Explosion Hazards

Material may splatter above 100C/212F.

Extinguishing Media

In case of fire, use water spray (fog) foam, dry chemical, or CO2.

Fire Fighting Instructions

In the event of a fire, firefighters should wear full protective clothing and NIOSH-approved self-contained breathing apparatus with a full facepiece operated in the pressure demand or other positive pressure mode.

6. Accidental Release Measures

Avoid release to the environment. Use appropriate Personal Protective Equipment (PPE). Contain spill and collect with absorbent material and transfer into suitable containers. Do not flush to sewer or allow to enter waterways. Ventilate enclosed area.

7. Handling And Storage

Handling And Storage Precautions

Keep containers tightly closed. Keep out of reach of children.

Work/Hygienic Practices

Wash thoroughly with soap and water after handling.

8. Exposure Controls/Personal Protection

Engineering Controls

Use with adequate general and local exhaust ventilation. Refer to the current edition of "Industrial Ventilation: A Manual of Recommended Practice" published by the American Conference of Governmental Industrial Hygienists for information on the design, installation, use, and maintenance of exhaust systems.

Eye/Face Protection

Faceshield over safety glasses or goggles.

Skin Protection

Chemical-resistant gloves. Lab coat or other work clothing to prevent skin exposure (Long sleeve shirt and long pants). Launder before reuse.

MATERIAL SAFETY DATA SHEET

SikaLatex R

8. Exposure Controls/Personal Protection - Continued

Respiratory Protection

A respirator protection program that meets 29 CFR 1910.134 requirement must be followed whenever workplace conditions warrant a respirator's use.

Other/General Protection

Wash thoroughly after handling.

Ingredient(s) - Exposure Limits

ACRYLIC POLYMER
OSHA PEL: NOT ESTABLISHED
ACGIH TLV: NOT ESTABLISHED
IARC: NO
NTP: NO

9. Physical And Chemical Properties

Appearance

Milky white liquid

Odor

Ammonia Odor

Chemical Type: Mixture

Physical State: Liquid

Melting Point: 32 °F 0 °C

Boiling Point: 212 °F 100 °C

Specific Gravity: 1.0 - 1.2

Percent Volatiles: 71-73 water

Vapor Pressure: 17mm Hg at 20C water

Vapor Density: <1 Water

pH Factor: N/AV

Solubility: N/AV

Evaporation Rate: < 1 Water

10. Stability And Reactivity

Stability: Stable

Hazardous Polymerization: Will not occur

Conditions To Avoid (Stability)

Avoid Freezing

Incompatible Materials

None Known

Hazardous Decomposition Products

None Known

11. Toxicological Information

Conditions Aggravated By Exposure

None Known

12. Ecological Information

No Data Available...

MATERIAL SAFETY DATA SHEET

SikaLatex R

13. Disposal Considerations

Dispose in accordance with applicable federal, state and local government regulations. Waste generators must determine whether a discarded material is classified as a hazardous waste. USEPA guidelines for the classification determination are listed in 40 CFR Parts 261.3. Additionally, waste generators must consult state and local hazardous waste regulations to ensure complete and accurate classification.

14. Transport Information

Proper Shipping Name

Not regulated by the USDOT.

15. Regulatory Information

U.S. Regulatory Information

All ingredients of this product are listed or are excluded from listing under the U.S. Toxic Substances Control Act (TSCA) Chemical Substance Inventory.

SARA Hazard Classes

Acute Health Hazard

SARA Section 313 Notification

This product does not contain any ingredients regulated under Section 313 of the Emergency Planning and Community Right-To-Know Act of 1986 or 40 CFR 372.

16. Other Information

HMIS Rating

Health: 1

Fire: 1

Reactivity: 0

PPE: B

Revision/Preparer Information

MSDS Preparer: EHS Department

MSDS Preparer Phone Number: 201-933-8800

This MSDS Supercedes A Previous MSDS Dated: 05/13/2002

Disclaimer

The data in this Material Safety Data Sheet relates only to the specific material herein and does not relate to use in combination with any other material or in any process. The information set forth herein is based on technical data that Sika believes to be reliable as of the date hereof. Since conditions of use are outside our control, we make no warranties, express or implied and assume no liability in connection with any use of this information. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

SIKA CORPORATION