

AC-20[®] +Silicone

Non-Sag, Acrylic Latex Caulking Compound

Specification Data Sheet



BASIC USES

• AC-20[®]'s elastomeric properties make it an excellent sealant for caulking interior concrete joints, hollow core ceiling and floor planks, window and door frames, vinyl, aluminum, steel and plywood siding, sheetrock, baseboards and bathroom and kitchen fixtures. It may be used to grout marble and ceramic tile, repair mortar joints, and, under controlled conditions, to bed insulated glass units and storm windows.

2. MANUFACTURER

Pecora Corporation

165 Wambold Road

Harleysville, PA 19438

Phone: 215-723-6051

800-523-6688

Fax: 215-721-0286

Website: www.pecora.com

3. PRODUCT DESCRIPTION

AC-20[®] is a pure acrylic latex sealant for general purpose interior and exterior caulking in architectural applications where slight to moderate movement is anticipated. Formulated with the highest quality ingredients including a silicone additive for greater adhesion and weatherability, AC-20[®] is completely compatible with premium-grade latex and oil paints and will not stain adjacent surfaces.

AC-20[®] has superb color stability and resistance to ultraviolet rays, ozone and airborne contaminants. It is mildew resistant and has United States Department of Agriculture acceptance for use in meat and poultry processing plants. In addition to the substrates listed above, AC-20[®] is compatible with polystyrene, polyurethane, cork, foamed and fibrous glass and gypsum board.

Limitations:

The sealant must be protected from water for 24 hours after application; do not caulk outdoors when rain is imminent.

Windows must be properly weeped since entrapped water could cause reversion. Sealant must be given additional time to fully cure before windows are installed because of the closed-in conditions.

PACKAGING

- 10.1 fl. oz. (.300 L) plastic cartridges
- 30 fl. oz. (.887 L) fiber cartridges
- 5-gallon (18.9 L) pails
- 55-gallon (208 L) drums

COLOR

- Black, Ivory, Limestone, Brown, Bronze, Cedar, Almond, Tan, Beige-Grey, Tru-White and Aluminum Stone

4. TECHNICAL DATA

Applicable Standards: AC-20[®] exceeds the requirements of ASTM C834 Specification For Latex Sealants.

Movement Capability: 7-1/2% in extension, 7-1/2% in compression (15%) when installed in properly designed joints within its range of thermal movement capabilities. Refer to Test Data Box below for further technical information.

Joint Design: The width of the joint should be approximately 12 times the anticipated movement and should fall within the range of 1/4" (6 mm) to 3/4" (19 mm). The depth of the joints should be 1/4" (6 mm) minimum to 3/8" (9 mm) maximum.

TYPICAL PHYSICAL PROPERTIES at 77° F (25°C); 50% R.H.

Test Property	Value	Test Procedure
Adhesion loss (%)	0.5	ASTM C736
Artificial weathering		ASTM C732
Adhesion loss (%)	1.0	ASTM C732
Cracking	None	ASTM C732
Discoloration	None	ASTM C732
Slump	None	ASTM C732
Wash-out	None	ASTM C732
Elongation, ultimate (%)	400-500	ASTM D412
Extrudability (gram/sec)	9.8	ASTM C731
Low-temperature flexibility (pass/fail)	Pass	ASTM C734
100% Modulus (psi)	15-20	ASTM D412
Recovery (%)	90	ASTM C736
Slump (in/mm)	0.05/1.3	ASTM D2202
Stain Index	1.1	ASTM D2203
Tack-free time (pass/fail)	Pass	ASTM D2377
Tensile, ultimate (psi)	30-40	ASTM D412
VOC Content (g/L)	31	ASTM D3960
Volume Shrinkage (%)	21.9	ASTM C733

5. INSTALLATION

Surface Preparation: Contact area must be clean, sound and free of contaminating substances such as oil, grease, asphalt, tar, etc. Priming is not generally required. Dampness but not saturation or standing water in porous substrates can be tolerated.

Joint Backing: Joints greater than 3/8" (9 mm) should be filled to within 3/8" (9 mm) of the surface with either polyethylene or polyurethane backer rod, preferably of a non-gassing, non-absorbing type. Use a diameter that will compress about 25% when installed. In joints too shallow to take backer rod, use a bond breaker tape to prevent three-sided adhesion.

Application: Although the freezing point of AC-20 is considerably below 32° F (0°C), and the sealant can withstand five freeze-thaw cycles, for best performance protect it from severe cold and apply above 40° F (4°C) to lessen the possibility of frost in the joints. Fill joints completely and tool lightly to insure full contact to both sides of the joint and present a smooth surface.

As with any waterborne product, the cure time is dependent on ambient conditions. Low temperatures or high humidity will extend cure time, while higher temperatures or low humidity will accelerate the cure.

Painting: Sealant may be painted within 30-45 minutes after application with quality grades of latex or oil paints.

Cleaning: Water may be used to remove excess sealant from substrate and clean tools before cure; after cure, sealant must be removed with mechanical means.

Storage Life: At least one year when stored in unopened containers in dry areas below 80° F (26°C).

Precautions: AC-20® is non-flammable, non-toxic, non-irritating and environmentally safe. However, do not take internally. Refer to Material Safety Data Sheet for additional information.

**FOR PROFESSIONAL USE ONLY
KEEP OUT OF THE REACH
OF CHILDREN.**

6. AVAILABILITY AND COST

Pecora products are available from our plants and warehouses, or from stocking distributors in all major cities. For the name and telephone number of your nearest representative call one of our locations listed below or visit our website at www.pecora.com.

7. WARRANTY

Pecora Corporation warrants its products to be manufactured free of defects. Under this warranty, we will provide, at no charge, replacement materials for, or refund the purchase price of, any product proven to be defective when installed in accordance with or published recommendations and in applications considered by us as suitable for this product. This warranty is in lieu of any and all other warranties, expressed or implied, and in no case will Pecora be liable for incidental or consequential damages.

8. MAINTENANCE

If the sealant is damaged and the bond is intact, cut out the damaged area and recaulk. No primer is necessary. If the bond has been affected, remove the sealant, clean and prepare the joint in accordance with instructions under "Installation."

9. TECHNICAL SERVICES

Pecora representatives are available to assist you in selecting an appropriate product and to provide on-site application instructions or to conduct jobsite inspections. For further assistance call our Technical Service Department at 800-523-6688.

10. FILING SYSTEMS

- Sweet's Catalog File: www.sweets.com
- General Building
 - 07100 Waterproofing
 - 07920 Sealants
- Civil Engineering
 - 07100 Waterproofing



**PECORA
CORPORATION**

P E O P L E • P R O D U C T S • P E R F O R M A N C E

HARLEYSVILLE, PA

165 Wambold Road, Harleysville, PA 19438
Phone: 800-523-6688 • 215-723-6051 • FAX: 215-721-0286

DALLAS, TX

11501 Hillguard Road, Dallas, TX 75243
Phone: 800-233-9754 • 214-348-5313 • FAX: 214-348-5421

www.pecora.com