

EUCO QWIKJOINT 200

POLYUREA FLOOR JOINT FILLER

DESCRIPTION

EUCO QWIKJOINT 200 is a fast-setting, semi-rigid polyurea used for filling control and construction joints in industrial concrete floors. EUCO QWIKjoint 200 represents a new generation of polyurea technology with features and benefits unlike any other polyurea joint filler on the market. Among these benefits are a super-fast set time and an extended shave time: EUCO QWIKjoint 200 can be trimmed flush with the floor immediately after placement or up to 24 hours later. EUCO QWIKjoint 200 supports and protects joint edges from heavy loads and wheel traffic, reducing spalling of the joint edges.

PRIMARY APPLICATIONS

- Concrete construction and control joints
- Crack repair for old floors
- Industrial and commercial floors
- Freezer floors

FEATURES/BENEFITS

- Fast setting formula reduces downtime
- Large shave time window allows for greater flexibility in scheduling joint filling operations
- No bubbles - no foaming
- Tough performance reduces floor joint repairs and maintenance
- Suitable for filling cracks in older floors to reduce the rate of joint deterioration
- Will cure in temperatures as low as -20° F (-29°C)
- Less moisture-sensitive than standard polyureas

TECHNICAL INFORMATION

Typical Engineering Data

Tack Free Time @70°F (23°C) 1 to 3 min

Light Traffic @70°F (23°C) 15 min

Full Traffic @70°F (23°C) 30 min

Tensile Strength

ASTM D 412 > 800 psi (>5.52 MPa)

Elongation ASTM D 412 200 to 250%

Tensile Modulus

ASTM D 412 600 to 675 psi (4.65 MPa)

Shore D Hardness ASTM D 2240 32 to 38

Shore A Hardness ASTM D 2240 88 to 90

Chemical Ratings: **Poor** - affected within 24 hours

Good - no effect for 24 hours

Excellent - no effect after 2 weeks

Chemical Resistance:

Acetic Acid, 5%excellent

Alcohol, 10%excellent

Alkaliesexcellent

Ammonium Hydroxide, 10 %excellent

Brake Fluid good

Diesel Fuel.....excellent

Ethylene Glycol good

Gasolineexcellent

Hydrochloric Acid, 20%excellent

JP-4 Jet Fuel.....excellent

Motor Oil.....excellent

Salt Waterexcellent

Sodium Hydroxide, 10%excellent

Sulfuric Acid,10% good

Xylene..... poor

Appearance: EUCO QWIKjoint 200 is a two part product available in gray or Mocha Brown. Part A is transparent amber and the Part B is pigmented gray or Mocha Brown. The user should expect some batch to batch variability in color. Product may yellow and discolor over time if exposed to either natural or artificial ultraviolet light.

PACKAGING

EUCO QWIKjoint 200 is a two part product packaged in 10 gal (37.9 L) kits, 100 gal (379 L) kits and 22 oz (600 mL) side-by-side cartridges, packaged 12 per case. The mix ratio for 10 gal kits, 100 gal kits and cartridges is 1:1.

SHELF LIFE

1 year in original, unopened package.

SPECIFICATIONS/COMPLIANCES

- EUCO QWIKjoint 200 complies with ACI 302 performance recommendations regarding control and construction joint fillers.
- USDA compliant



The Euclid Chemical Company

19218 Redwood Rd. • Cleveland, OH 44110

Phone: [216] 531-9222 • Toll-free: [800] 321-7628 • Fax: [216] 531-9596

www.euclidchemical.com

An **RPM** Company



COVERAGE

The following table gives guidelines on theoretical material estimates in linear ft/gal (liner m/L).

Joint Width	Joint Depth		
	1.5"(38 mm)	2"(51 mm)	2.5"(63 mm)
3/16" (4.8 mm)	68' (5.5 m)	51' (4.2 m)	41' (3.2 m)
1/4" (6.4 mm)	51' (4.2 m)	38' (3.2 m)	30' (2.4 m)
3/8" (9.5 mm)	34' (2.6 m)	25' (2.1 m)	20' (1.6 m)

DIRECTIONS FOR USE

Surface Preparation: The joint must be clean and dry. All oil, dirt, debris, paint and any other material that may be a bond breaker must be removed. The final step in cleaning should be the complete removal of all residue with a vacuum cleaner or pressure washing. All joint facings must possess an open surface texture with all curing compounds and sealers removed. If this product will be used for filling floor cracks, the cracks should be routed out and cleaned before filling. Ideally, all edges will be squared.

Joint Backing: The Euclid Chemical Company recommends the full depth of the joint or crack be filled with EUCO QWIKjoint 200 for proper load transfer. Avoid the use of backer rod, sand or other fill material for the purpose of reducing volume.

Priming: EUCO QWIKjoint 200 does not require a primer before application.

Mixing: Due to its extremely fast set time, EUCO QWIKjoint 200 requires machine mixing and placing. **Pre-mix Part B separately before using.** Follow mechanical pump manufacturer's equipment instructions for operation. QWIKjoint 200 cartridges should be shaken before using, as some settlement is normal during storage. Follow the specific installation instructions on the cartridge label.

Note: If EUCO QWIKjoint 200 is to be stored in the dispensing pump overnight, place a piece of plastic sheeting directly on top of the material in each tank to prevent exposure to air. EUCO QWIKjoint 200 Part B thickens upon standing, but can be thinned back to a normal consistency by gentle mixing with a drill or by hand.

Placement: Euclid Chemical recommends full depth placement. Joints should be overfilled and shaved even with the surrounding joint edge giving the floor joints a flat, smooth appearance. Shaving of excess EUCO QWIKjoint 200 can begin approximately 30 minutes after placement, and up to 24 hours later, depending on jobsite conditions such as the concrete and ambient temperatures.

CLEAN-UP

Tools, equipment and general clean-up can be done with EUCO SOLVENT, acetone or toluene. Clean equipment before EUCO QWIKjoint 200 has dried or cured.

PRECAUTIONS/LIMITATIONS

- **Based on ACI 302 recommendations, joint fillers should be applied as late as possible after construction to allow for minimal additional slab shrinkage. Consult ACI 302 comments regarding concrete shrinkage, joint filling and user expectations.**
- Proper joint design will affect performance.
- Do not use EUCO QWIKjoint 200 as an expansion joint sealant.
- Contact surfaces must be clean and dry for best adhesion.
- Joint edges must be thoroughly cleaned prior to filling, particularly if a floor sealer has been applied.
- Product is designed for use in joints with minimal movement.
- Product may discolor in direct sunlight or artificial light.
- Do not use in large movement (expansion/isolation) joints.
- In all cases, consult the Material Safety Data Sheet before use.

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.