

EUCOCRETE

HIGH PERFORMANCE REPAIR MATERIAL WITH CORROSION INHIBITOR

DESCRIPTION

EUCOCRETE is a versatile, one part, microsilica modified patching and repair compound that contains an integral corrosion inhibitor for concrete repair projects of all types. Requiring only the addition of water, EUCOCRETE is a high strength material with an extended working time for ease of placement. It is similar in appearance to concrete and is suitable for use as a topping, patching mortar or repair material on concrete structures from 1 to 6 inches (25 to 152 mm) deep.

PRIMARY APPLICATIONS

- Parking decks
- Joint repairs
- Balconies
- Equipment bases
- Floor toppings
- Pedestals
- Beams
- Pavements

FEATURES/BENEFITS

- Microsilica modified for high strength
- Premixed with pea gravel, ready-to-use
- Low permeability with excellent freeze/thaw resistance
- Long working time
- Compatible with galvanic anodes
- Interior or exterior
- Contains an integral corrosion inhibitor
- ▲ Can contribute to LEED points

TECHNICAL INFORMATION

Typical Engineering Data @70°F (21°C)

Compressive Strength ASTM C 109, 2" (50 mm) cubes @ 0.5gal/50 lb bag.

Age	Strength
1 day.....	5,300 psi (37 MPa)
3 days.....	6,640 psi (46 MPa)
7 days.....	8,800 psi (61 MPa)
28 days.....	9,750 psi (67 MPa)

Compressive Strength ASTM C 39, 3"x6" cyl. @ 0.5gal/50lb. bag.

1 day.....	5,000 psi (34 MPa)
3 days.....	6,080 psi (42 MPa)
7 days.....	7,400 psi (51 MPa)
28 days.....	8,950 psi (62 MPa)

Freeze/Thaw Resistance ASTM C-666 Procedure A 1000 Cycles..... 99% relative dynamic modulus

Flexural Strength ASTM C 348*

7 days.....	2,000 psi (9 MPa)
28 days.....	2,300 psi (10 MPa)

Rapid Chloride Permeability ASTM C 1202

28 days.....	1000 coulombs
56 days.....	900 coulombs

Working Time 2 hrs 30 min

Consistency:

Initial slump.....	10" (254 mm)
30 minute slump.....	9.5" (241 mm)
1 hour slump.....	9" (229 mm)

Set Time ASTM C 403

Initial.....	3 hrs 40min
Final.....	4 hrs 40min

Unit Weight.....146.41 lb/ft³ (2345.49 kg/m³)

Volumetric Resistivity.....15,400 Ω/cm

EUCOCRETE is a free flowing powder designed to be mixed with water. After mixing and placing, the color may initially appear somewhat darker than the surrounding concrete. While this color will lighten up substantially as the concrete cures and dries out, the repair may always appear slightly darker than the surrounding concrete.

PACKAGING/YIELD

EUCOCRETE is packaged in 50 lb (22.7 kg) bags. **Yield:** 0.37 ft³ (0.01m³) per bag when mixed with 0.5 gal (1.9 L) of water. Bulk bags suitable for mixing in R/M transit trucks are also available.

SHELF LIFE

2 years in original, unopened package.

COVERAGE

One unit of EUCOCRETE will cover approximately 4.5 ft² (0.42 m²) when placed at an average depth of 1" (2.5 cm). EUCOCRETE may be extended with up to 15 lbs (6.8 kg) of 3/8" (9.5 mm) pea gravel for placements over 6" (15 cm), which will yield 0.46 ft³ (0.013 m³). This may alter certain engineering properties. Contact The Euclid Chemical Company for additional information.



The Euclid Chemical Company

19218 Redwood Rd. • Cleveland, OH 44110
Phone: [216] 531-9222 • Toll-free: [800] 321-7628 • Fax: [216] 531-9596
www.euclidchemical.com

An **RPM** Company



DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP 5-7 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

Priming: Clean and prime exposed steel with DURALPREP AC. Concrete should be primed with a spray or brush coat of DURALPREP AC. Alternately, a Saturated Surface Dry (SSD) concrete surface can be primed with a scrub coat of EUCOCRETE. The repair must be made before the scrub coat dries out.

Mixing: Single bags may be mixed with a drill and “jiffy” mixer. Use a paddle type mortar mixer for large jobs. All materials should be in the proper temperature range of 60°F (15°C) to 90°F (32°C). Add the appropriate amount of water, .45 - .50 gal (1.7 - 1.9L) per bag, for the batch size and then add the dry product. Mix a minimum of 3 minutes. If additional pea gravel is to be added, do so now and mix an additional 2 to 3 minutes. The mixed product should be transported to the repair area and placed immediately.

Placement: For patching, spread with a trowel, come-a-long, or square tipped shovel to a thickness that matches the surrounding concrete. Finish to desired texture. Note: On large floor areas, use screed strips as guides in combination with vibratory screeding to level. Compact and finish by hand or machine trowel.

Finishing: This product is designed for finishing with a float or broom appearance. A steel trowel finish may be applied but timing of the final trowel is critical and the contractor may have difficulty achieving a smooth finish over a large area. Do not add additional water to the surface during the finishing operation; use EUFOBAR finishing aid.

Curing and Sealing: To prevent surface cracking, cure the floor with a high solids curing compound from The Euclid Chemical Company. In hot, windy or direct sunlight situations, re-wet the surface after the curing compound has dried and cover with polyethylene for a minimum of three days. If a curing compound is not desired, wet cure for a minimum of three days.

CLEAN-UP

Clean tools and equipment with water before the material hardens.

PRECAUTIONS/LIMITATIONS

- Do not use material at temperatures below 45°F (7°C).
- No heavy traffic until the product has cured.
- Keep repair from freezing until a minimum strength of 1000 psi (6.90 MPa) is reached.
- EUCOCRETE requires a primer bond coat and a curing compound.
- In all cases, consult the Material Safety Data Sheet before use.

Rev. 02.11

WARRANTY: The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.