

FLAME RETARDANT POLYETHYLENE FILM

IDEALLY SUITED FOR ANY APPLICATION REQUIRING A PROTECTIVE COVERING WITH FLAME RETARDANT CHARACTERISTICS

TEST RESULTS*

		4 MIL	6 MIL
BURNING CHARACTERISTICS	ASTM E 84		
FLAME SPREAD INDEX		10	10
SMOKE DEVELOPMENT		45	60
TENSILE STRENGTH	ASTM D 882		
MD		1700 psi	1700 psi
TD		1200 psi	1200 psi
ELONGATION	ASTM D 887		
MD		225%	225%
TD		350%	350%
DART IMPACT	ASTM D 1709	165 g	260 g
WATER VAPOR TRANSMISSION RATE	ASTM E 96	.19 perm	.13 perm

*Meet or exceed standard specifications for Up North Plastics standard construction films.

STOCK SIZES					
STOCK#	WIDTH	LENGTH	GAUGE	WT/ROLL	ROLL/PLT
4100FR	8'4"	100'	.004	15.9	64
412FR	12'	100'	.004	22.9	49
420FR	20'	100'	.004	38.2	30
620ASFR	20'	100'	.006	57.4	20
620FR	20'	100'	.006	57.4	20

**CUSTOM SIZES AVAILABLE
FOR CURRENT PRICING AND DELIVERY CALL
800-544-7659**