



PRODUCT SUBMITTAL



Series 200 Ladder Mesh (For Single Wyth Wall)



16" O.C. cross rods allow core clearance.

ASTM A82 / A82M - (Cold drawn steel wire)
 Tensile Strength - 80,000 psi
 Yield Point - 70,000 psi
ASTM A951 / A951M-06 - (Standard Specification for Steel Wire for Masonry Joint Reinforcement)
ACI / ASCE 530 - (Building code requirements for masonry structures)
 Mill Galvanized / Zinc Coating: **ASTM A641 / A641M** (0.10 oz per sq ft)
 Hot Dip Galvanized after fabrication / Zinc Coating
ASTM A153 / A153M-B2 (1.50 oz per sq ft)
 Stainless Steel **ASTM 580 / ASTM 580M** Type 304 (Type 316 available on special order)



WIRE Recycled Content:
 Mill Galvanized & Hot Dip,
 85% Post-Consumer
 13% Post Industrial / Pre - Consumer
 Stainless Steel,
 60% Post Consumer
 V O C Content - 0%

- Mill Galvanized / Zinc Coating: **ASTM A641 / A641M** (0.10 oz per sq ft)
- Hot Dip Galvanized after fabrication / Zinc Coating
ASTM A153 / A 153 - B2 (1.50 oz per sq ft)
- Stainless Steel **ASTM 580 / ASTM 580M** Type 304 (Type 316 available on special order)

WIRE SIZE:	<u>Side Rods</u>	<u>Cross Rods</u>
<input checked="" type="checkbox"/> Standard	9 Gauge (.148 in)	9 Gauge
<input type="checkbox"/> Heavy Duty	3/16" (.187 in)	9 Gauge
<input type="checkbox"/> Extra Heavy Duty	3/16" (.187 in)	3/16"

Corporate Office: 400 Roundtree Rd Charlotte, NC 28217
 TEL: (800) 849-6722 FAX: (704) 525-3761

Mailing Address: P.O. Box 240988 Charlotte, NC 28224



www.wirebond.com

Memphis Plant: 2365 Harbor Ave. Memphis, TN 38113
 TEL: (800) 441-8359 FAX: (901) 775-9449

Mailing Address: P.O. Box 13124 Memphis, TN 38113