

<b>REPORT OF MORTAR MIX DESIGN</b>
------------------------------------

**MORTAR TYPE:** N Property

**MIX DESIGNATION:** TCC BOM 101212, 100316

**RECOMMENDED LOCATION:** Exterior, Above Grade Masonry Veneer

**BUILDING SEGMENT:** Refer to ASTM C 270

**MATERIALS:**

Portland Cement	ASTM C 150, TYPE I
Hydrated Lime	ASTM C 207, TYPE S
Natural Sand	ASTM C 144

<b>MORTAR PROPERTIES:</b>		<b>ASTM C 270 Requirements:</b>
Compressive Strength	1450 psi	750 psi average at 28 days
Water Retention	92%	75% minimum
Air Content	5.30%	12% maximum
Aggregate Ratio	3.09	2¼ to 3½

**TESTING FACILITY:** Cemstone Companies Materials Laboratory

Date: 8-Jan-09

LAB ID: T081209B

- NOTES:**
- This mortar meets the property requirements for Type N masonry mortar as defined in Specification C 270.
  - Field sampling and testing of mortar is conducted under Test Method C 780 and is used to verify consistency of the materials and procedures, not mortar strength. ACI 530.1 - 92/ASCE 6-92/TMS 602-92

*Reviewed By:*

---

*Kevin A. MacDonald, Ph.D., P.E.*