

## SEALMASTIC™ EMULSION

### Dampproofings

#### DESCRIPTION

SEALMASTIC Emulsion-Type Dampproofings are the breather-type which permit moisture vapor to escape through the film while remaining resistant to water penetration. This prevents blistering of applied films. They can be applied to green concrete (not totally dry).

TYPE I-SPRAY GRADE is an asphalt-base, non-fibred, clay emulsion. Under normal use, it resists flow or sag. Its greater resistance to water is ideal, where spray application is desired.

TYPE II-BRUSH-ON/SPRAY GRADE is an asphalt-base, clay emulsion with fibers specifically formulated to offer a tight film that combines both excellent strength and resistance to water.

TYPE III-TROWEL-ON-GRADE is a trowel-applied mineral colloid; asphalt emulsion fibred with selected fibers and produced in an ideal, light trowel application consistency. TYPE III offers high weather, water, corrosion and abrasion resistance. It can be used as an adhesive on foam board installations.

All SEALMASTIC products meet the VOC content limits of 500 g/L for Bituminous Coatings and Mastics as required by the U.S. EPA Architectural Coatings Rule.

#### USES

SEALMASTIC Emulsion-type Dampproofing Coatings are ideal for reducing dampness and moisture infiltration through foundation walls, parapets, fire walls, tanks, culverts, cisterns and bridge abutments. They are also applicable for stone-backing, above-grade cavity wall applications and below-grade masonry wall dampproofing. The SEALMASTIC product line also helps to minimize internal structural damage from mildew and mold.

#### PACKAGING

5 Gallon (18.93 Liter) Pails  
55 Gallon (208.20 Liter) Drums

#### SPECIFICATIONS

TYPE I-Spray Grade ASTM D 1187, Type I  
ASTM D 1227, Type III, Class 1

TYPE II-Brush-On or  
Spray Grade ASTM D 1227, Type II, Class 1

TYPE III -Trowel-On  
Grade ASTM D 1227, Type II, Class 1

#### FEATURES AND BENEFITS

- Adheres to damp or "green" surfaces...no waiting for concrete to thoroughly dry
- Ready-to-use...no heating or thinning required, dries rapidly
- Fast and economical way to protect concrete and masonry foundation walls from moisture penetration
- Easy-to-apply...available in spray, brush or trowel grades, meets a broad application range
- Three application grades available for maximum versatility
- VOC compliant...meets the U.S. EPA Architectural Coatings Rule requirements

#### \*COVERAGE

##### TYPE I

Above Grade Surfaces: Approximately 70-100 sq. ft./gal. (1.71 to 2.45 sq. m/L) per coat.

##### TYPE II & TYPE III

Exterior Below Grade Dense Surfaces, Exterior Below Grade Porous Surfaces, Interior Above Grade Surfaces:

(One coat, 1/8" wet film thickness): Approximately 10-12.5 sq. ft./gal (0.25 to 0.3 sq. m/L)

(One coat, 1/16" wet film thickness): Approximately 20-25 sq. ft./gal (0.5-0.6 sq. m/L).

\*Coverage may vary due to porosity and condition of concrete.

**ADDITIONAL DAMPPROOFING PRODUCTS FROM  
W. R. MEADOWS CAN BE FOUND BY VISITING  
OUR WEBSITE: [www.wrmeadows.com](http://www.wrmeadows.com)**

*CONTINUED ON REVERSE SIDE...*

### Application Tools



Trowel



Soft Bristle Brush



Electric Drill  
with Jiffy Mixer



Ratio Pump



Wire Brush

### APPLICATION / DIRECTIONS

**SURFACE PREPARATION...**All surfaces to be coated must be thoroughly cleaned of all scale, loose mortar, dust, rust, dirt, oil, grease and other foreign matter. Use a wire brush, sandblast or other methods in keeping with good construction practices. Before product application, fill voids, cracks and holes in concrete with cement mortar and allow to dry. If primer is required, use SEALMASTIC SPRAY-MASTIC from W. R. MEADOWS. Do not apply when temperatures below 35°F (2°C) are anticipated. Do not apply in rain or when rain is threatening.

**MIXING...**TYPE I (Spray Grade) and TYPE II (Brush or Spray Grade) should be thoroughly stirred in their respective containers prior to application. TYPE III (Trowel Grade) can be applied directly from the container.

### EXTERIOR BELOW-GRADE DENSE SURFACES

Apply TYPE II (Brush or Spray Grade) by soft bristle brush or suitable spray equipment\* or TYPE III by trowel.

Dampproofings should be applied to properly prepared surfaces in a continuous, unbroken film, free of pinholes, filling and spreading around all joints, slots and grooves and penetrating into all crevices, chases, reveals, soffits and corners. Carry coating over the exposed footing's top and outside edge up to finished grade.

**NOTE:** Fillers, extenders and additives in concrete mixes can produce a higher than normal porosity and as a result, additional coverage coats may be required.

\*Consult spray equipment manufacturer for instructions.

### EXTERIOR BELOW-GRADE POROUS SURFACES (3) OPTIONS

- 1. MEMBRANE SYSTEM:** For severe conditions or for added protection, apply one coat of TYPE II (Brush or Spray Grade) or TYPE III (Trowel Grade).

Within four hours, apply a glass fabric membrane cloth over all coating surfaces. Overlap all edges by 3" (76mm) minimum. Press firmly into place without wrinkles. Application of the second coat of TYPE II or TYPE III should be within 24 hours.

- 2. TWO-COAT SYSTEM:** Apply SEALMASTIC SPRAY-MASTIC as a prime coat. Allow coat to dry tacky to touch and then apply TYPE III in one coat, as described under Dense Surface Application.

- 3. PARGE COAT SYSTEM:** Before application of SEALMASTIC DAMPPROOFINGS, a parge coat of cement mortar should be applied to the block wall. This coat should cover the bottom of the footings to grade level, forming a cove at the junction of the wall and footing. Once the parge coat cures, apply one trowel coat of TYPE III or two spray or brush coats of TYPE II, as described under Dense Surface Application.

### BACKFILLING

Backfilling should be done within 24 to 48 hours after application. No longer than seven days maximum should elapse. Be careful not to damage or rupture the film or displace coating or membranes. To assure maximum protection, W.R. MEADOWS Protection Board should be used. Prolonged exposure to ultraviolet sunrays should be minimized.

### INTERIOR ABOVE-GRADE SURFACES-VAPOR RETARDER

TYPE I (Spray Grade), TYPE II (Brush or Spray Grade) and TYPE III (Trowel Grade) can be used individually or in combination for dampproofing the exterior face of interior walls in cavity wall construction.

**CLEAN UP...** While still wet, material may be removed with soap and water. Once dried, the material can be removed with kerosene or petroleum naphtha. Solvent manufacturer precautions should be adhered to when using a solvent for clean up.

### PRECAUTIONS

Keep from freezing in the original container. Read and follow application information and precautions. Refer to Material Safety Data Sheet for complete health and safety information.

**TO VERIFY MOST RECENT TECHNICAL DATA SHEET IS BEING USED, VISIT OUR WEBSITE: [www.wrmeadows.com](http://www.wrmeadows.com)**

### LIMITED WARRANTY

"W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order." Read complete warranty. Copy furnished upon request.

### Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no

control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

