

# Sikaflex<sup>®</sup>-2c NS

Two-component, non-sag, polyurethane elastomeric sealant

<b>Description</b>	Sikaflex-2c NS is a 2-component, premium-grade, polyurethane-based, elastomeric sealant. It is principally a chemical cure in a <u>non-sag</u> consistency. Meets ASTM C-920, Type M, Grade NS, Class 25, use T, NT, M, G, A, O, I and Federal Specification TT-S-00227E, Type II, Class A. Tested in accordance with ASTM C-1382 for use in EIFS Systems.
<b>Where to use</b>	<ul style="list-style-type: none"> <li>■ Intended for use in all properly designed working joints with a minimum depth of 1/4 inch.</li> <li>■ Ideal for vertical and horizontal applications.</li> <li>■ Placeable at temperatures as low as 40°F.</li> <li>■ Adheres to most substrates commonly found in construction.</li> <li>■ An effective sealant for use in Exterior Insulation Finish Systems (EIFS).</li> <li>■ Submerged environments, such as canal and reservoir joints.</li> </ul>
<b>Advantages</b>	<ul style="list-style-type: none"> <li>■ Capable of ±50% joint movement.</li> <li>■ Chemical cure allows the sealant to be placed in joints exceeding ½ in. in depth.</li> <li>■ High elasticity with a tough, durable, flexible consistency.</li> <li>■ Exceptional cut and tear resistance.</li> <li>■ Exceptional adhesion to most substrates without priming.</li> <li>■ Available in 40 architectural colors.</li> <li>■ Color uniformity assured via Color-pak system.</li> <li>■ Available in pre-pigmented Limestone Gray (no Color-pak needed).</li> <li>■ Non-sag even in wide joints.</li> <li>■ Easy to mix.</li> <li>■ Paintable with water-, oil-, and rubber-base paints.</li> <li>■ ANSI/NSF 61 approval for contact with potable water.</li> <li>■ Jet fuel resistant</li> </ul>
<b>Coverage</b>	1 gal. yields 231 cu. in. or 154 lin. ft. of a 1/2 in. x 1/4 in. joint.
<b>Packaging</b>	1.5 gal. unit, 3 gal unit. Color-pak is purchased separately. Limestone Gray color available pre-pigmented.

**Typical Data (Material and curing conditions 73°F(23°C) and 50% R.H.)**

<b>Shelf life</b>	One year in original, unopened containers.	
<b>Storage Conditions</b>	Store dry at 40°-95°F (4°-35°C). <b>Condition material to 65°-75°F before using.</b>	
<b>Colors</b>	A wide range of architectural colors are available. Special colors available on request.	
<b>Application Temperature</b>	40° to 100°F, ambient and substrate temperatures. Sealant should be installed when joint is at mid-range of its anticipated movement.	
<b>Service Range</b>	-40° to 170°F (-40°-75°C).	
<b>Curing Rate (ASTM C-679)</b>		
Tack-Free Time	6-8 hrs.	
Final Cure	3 days	
<b>Application Life</b>	3-4 hrs.	
<b>Tear Strength</b>	ASTM D-624	45 lb./in.
<b>Shore A Hardness</b>	ASTM D-2240	25 ± 5
<b>Tensile Properties (ASTM D-412)</b>		
Tensile Strength at Break	120 psi	
Tensile Elongation	500%	
100% Modulus	70 psi	
<b>Adhesion in Peel (Fed Spec. TT-S-00227E)</b>		
<b>Substrate</b>	<b>Peel Strength</b>	<b>% Adhesion Loss</b>
Concrete	25 lb.	Zero
<b>Weathering Resistance</b>	Excellent	
<b>Chemical Resistance</b>	Good resistance to water, diluted acids, diluted alkalines, and residential sewage. Consult Technical Service for specific data.	



## How to Use

### Surface Preparation

All joint-wall surfaces must be clean, sound, and frost-free. Joint walls must be free of oils, grease, curing compound residues, and any other foreign matter that might prevent bond. Ideally this should be accomplished by mechanical means. Bond breaker tape or backer rod must be used in bottom of joint to prevent bond.

### Priming

Priming is typically not necessary. Most substrates only require priming if sealant will be subjected to water immersion after cure. Testing should be done, however, on questionable substrates, to determine if priming is needed. Consult Technical Service or Sikaflex Primer Technical Data Sheet for additional information on priming.

**Note:** Most Exterior Insulation Finish Systems (EIFS) manufacturers recommend the use of a primer. When EIFS manufacturer specifies a primer or if on-site bond testing indicates a primer is necessary, Sikaflex 429 primer is recommended. On-site adhesion testing is recommended with final system prior to the start of a job.

### Mixing

Pour entire contents of Component 'B' into pail of Component 'A'. Add entire contents of Color-pak into pail and mix with a low-speed drill (400-600 rpm) and Sikaflex paddle.\* Mix for 3-5 minutes to achieve a uniform color and consistency. Scrape down sides of pail periodically. Avoid entrapment of air during mixing.

When mixing in cold weather (<50°F), do not force the mixing paddle to the bottom of the pail. After adding Component 'B' and Color-pak into Component 'A', mix the top 1/2 to 3/4 of the pail during the first minute of mixing. After scraping down the sides of the pail, mix again for another minute. The paddle should reach the bottom of the pail between the first and second minute of mixing. Scrape down the sides of the pail a second time and then mix for an additional 2-3 minutes until the sealant is well blended.

**Color-pak must be used with tint base. For pre-pigmented Limestone base, just mix with low speed drill and Sikaflex paddle (no Color-pak needed).**

### Application

Recommended application temperatures 40°-100°F. Pre-conditioning units to approximately 70°F is necessary when working at extremes. Move pre-conditioned units to work areas just prior to application.

Apply sealant only to clean, sound, dry, and frost-free substrates. Sikaflex-2c should be applied into joints when joint slot is at mid-point of its designed expansion and contraction.

To place, load directly into bulk gun or use a follower plate loading system. Place nozzle of gun into bottom of joint and fill entire joint. Keeping the nozzle deep in the sealant, continue with a steady flow of sealant preceding nozzle to avoid air entrapment. Also, avoid overlapping of sealant since this also entraps air. Tool as required. Joint dimension should allow for 1/4 inch minimum and 1/2 inch maximum thickness for sealant. Proper design is 2:1 width to depth ratio.

### Limitations

- The ultimate performance of Sikaflex-2c NS depends on good joint design and proper application.
- Minimum depth in working joint is 1/4 in.
- Maximum expansion and contraction should not exceed 50% of average joint width.
- Do not cure in the presence of curing silicones.
- Avoid contact with alcohol and other solvent cleaners during cure.
- Allow 3-day cure before subjecting sealant to total water immersion.
- Avoid exposure to high levels of chlorine. (Maximum level is 5 ppm).
- Do not apply when moisture vapor transmission exists since this can cause bubbling within the sealant.
- Avoid over-mixing sealant.
- Light color shades tend to yellow over time when exposed to ultraviolet rays.
- Light colors can yellow slightly if exposed to direct gas fired heating elements prior to the formation of initial skin.
- When overcoating: an on-site test is recommended to determine actual compatibility.
- The depth of sealant in horizontal joints subject to traffic is 1/2 inch.
- In horizontal joints exposed to vehicular or foot traffic, "TG" additive is recommended. See Sikaflex-2c NS TG data sheet for specific details.

### Caution

**Component 'A'; Irritant** - Avoid contact. Product is a skin, respiratory and eye irritant. Use of safety goggles and chemical resistant gloves recommended. Use of a NIOSH approved respirator required if PELs are exceeded. Use with adequate ventilation.

**Component 'B'; Combustible; Sensitizer; Irritant** - Contains Xylene. Keep away from heat, sparks and open flame. Use with adequate ventilation. Product is a respiratory and skin sensitizer. Avoid contact. Product is an eye, skin, and respiratory irritant. Use of safety goggles and chemical resistant gloves recommended. Use of a NIOSH approved respirator required if PELs are exceeded.

### First Aid

In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with plenty of water for at least 15 minutes; contact physician. For respiratory problems, remove to fresh air. Wash clothing before re-use. Discard contaminated shoes.

### Clean Up

Uncured material can be removed with approved solvent. Cured material can only be removed mechanically. For spillage, collect, absorb, and dispose of in accordance with current, applicable local, state, and federal regulations.

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

KEEP OUT OF REACH OF CHILDREN

FOR INDUSTRIAL USE ONLY

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

Visit our website at [www.sikausa.com](http://www.sikausa.com)

1-800-933-SIKA NATIONWIDE

**Regional Information and Sales Centers.** For the location of your nearest Sika sales office, contact your regional center.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Corregidora, Queretaro  
C.P. 76920 A.P. 136  
Phone: 52 42 25 0122  
Fax: 52 42 25 0537

