



# Stego® Wrap Class A Vapor Retarder

STEGO INDUSTRIES, LLC



**Vapor Retarders**  
**07260, 03300**

### Manufacturer

Stego Industries, LLC  
216 Avenida Fabricante, Suite 101  
San Clemente, CA 92672  
Sales, Technical Assistance  
Ph: (877) 464-7834  
Fx: (949) 257-4113  
www.stegoindustries.com

### Product Description

**USES:** Stego Wrap Class A is used as an exceptional vapor retarder, and as a protection course for below grade waterproofing applications.

**COMPOSITION:** Stego Wrap Class A is a multi-layer plastic extrusion manufactured with only the highest grade of prime, virgin, polyolefin resins.

#### ENVIRONMENTAL FACTORS:

Stego Wrap Class A can be used in systems for the control of soil gases (radon, methane), soil poisons (oil by-products) and sulfates.

### Installation

**UNDER SLAB:** Unroll Stego Wrap Class A over an aggregate, sand or tamped

earth base. Overlap all seams a minimum of six inches and tape using Stego Tape. All penetrations must be sealed using a combination of Stego Wrap Class A, Stego Tape and/or Stego Mastic.

**VERTICAL WALL:** Install Stego Wrap Class A over the waterproofing membrane while still tacky. Mechanically fasten Stego Wrap Class A to the wall at the top with termination bar and concrete nails. Drape Stego Wrap Class A down across the footer and under the french drain.

### Availability & Cost

Stego Wrap Class A is available nationally via building supply distributors. For current cost information, contact your local Stego Wrap distributor or Stego Industries' sales department.

### Warranty

Stego Industries, LLC believes to the best of its knowledge, that specifications and recommendations herein are accurate and reliable. However, since

site conditions are not within its control, Stego Industries does not guarantee results from the use of the information provided and disclaims all liability from any loss or damage. No warranty, express or implied, is given as to the merchantability, fitness for a particular purpose, or otherwise with respect to the products referred to.

### Maintenance

None required.

### Technical Services

Technical advice, custom CAD drawings, and additional information can be obtained by contacting Stego Industries' technical assistance department or via the website.

### Filing Systems

- Stego Industries' website
- Buildsite
- GreenFormat
- 4Specs

## Technical Data

**TABLE 1: PHYSICAL PROPERTIES OF STEGO WRAP CLASS A VAPOR RETARDER**

PROPERTY	TEST	RESULTS
Under Slab Vapor Retarders	ASTM E 1745 Class A, B & C – Standard Specification for Water Vapor Retarders Used in Contact with Soil or Granular Fill under Concrete Slabs	Exceeds Class A, B & C
Water Vapor Permeance	ASTM F 1249 – Test Method for Water Vapor Transmission Rate Through Plastic Film and Sheeting Using a Modulated Infrared Sensor	0.0223 perms
Puncture Resistance	ASTM D 1709 – Test Methods for Impact Resistance of Plastic Film by Free-Falling Dart Method	2266 grams
Tensile Strength	ASTM D 882 – Test Method for Tensile Properties of Thin Plastic Sheeting	53.2 lbf/in.
Permeance After Conditioning (ASTM E 1745 Sections 7.1.2 - 7.1.5)	ASTM E 154 Section 8, F 1249 – Permeance after wetting, drying, and soaking ASTM E 154 Section 11, F 1249 – Permeance after heat conditioning ASTM E 154 Section 12, F 1249 – Permeance after low temperature conditioning ASTM E 154 Section 13, F 1249 – Permeance after soil organism exposure	0.0243 perms 0.0264 perms 0.0223 perms 0.0257 perms
Chemical Resistance	ASTM E 154 – Test Methods for Water Vapor Retarders Used in Contact with Earth under Concrete Slabs, on Walls, or as Ground Cover	Unaffected
Life Expectancy	ASTM E 154 – Test Methods for Water Vapor Retarders Used in Contact with Earth under Concrete Slabs, on Walls, or as Ground Cover	Indefinite
Thickness	ACI 302.1R-04 – Minimum Thickness (10 mils)	10 mils
Roll Dimensions		14 ft. wide x 210 ft. long or 2,940 ft <sup>2</sup>
Roll Weight		140 lbs.

Note: perm unit = grains/(ft<sup>2</sup> \*hr\* in.Hg)

