



THE EUCLID CHEMICAL COMPANY

19218 REDWOOD ROAD • Cleveland, OH 44110
(216) 531-9222 • (800) 321-7628 • FAX (216) 531-9596
www.euclidchemical.com

SURFHARD®



CHEMICAL HARDENER AND DUSTPROOFER FOR CONCRETE



SURFHARD† is a magnesium silicofluoride that reacts chemically with the free lime and calcium salts in hardened concrete to make a more dense and durable surface. It will effectively penetrate a concrete surface and make it hard, free from dusting and highly resistant to corrosion and abrasion. The addition of a patented penetrating agent to SURFHARD makes it possible for its penetrating properties and hardening action to proceed to a greater depth than with conventional hardeners.

PRIMARY APPLICATIONS

- Horizontal and vertical surfaces
- Schools
- Industrial floors
- Commercial buildings
- Home basements
- Storage silos in coal scrubbing facilities

FEATURES/BENEFITS

- Hardens and dustproofs concrete surfaces
- Prolongs floor life
- Resists acids, alkalis, oils and salts
- Simplifies cleaning
- Can be used without interrupting production schedules

SPECIFICATIONS/COMPLIANCES

- This product meets V.O.C. contents in accordance to EPA 40 CFR Part 59 Table I Subpart D for Concrete Protective Coatings with a maximum V.O.C. content of 400 g/l.

PACKAGING

SURFHARD is packaged in 55 gal (208 liter) drums, 5 gal (18.9 liter) pails.

Shelf Life: 2 years in original, unopened package.

†SURFHARD is a registered trademark no. 819,356

TECHNICAL INFORMATION

V.O.C.0 g/l

Typical Performance

Application	Cure Time
Foot traffic.....	4-6 hours
Wheel traffic.....	24 hours

SURFHARD helps protect concrete against the harmful effects of:

- Caustic soda
- Calcium chloride
- Sodium chloride
- Soap solutions
- Ammonium chloride
- Solvents
- Fuel oils
- Sugar solutions

Appearance

SURFHARD is a clear liquid which dries transparent. After placing, the color of the concrete may initially appear darker than the surrounding concrete. but as the sealer cures and dries out, the treated concrete will have little change in appearance. Treated concrete will slightly bead water and other liquids.

COVERAGE

SURFHARD is applied in up to three coats per the following recommended dilutions:

COAT	DILUTION
1st coat:	1 part SURFHARD to 2 parts water
2nd coat:	1 part SURFHARD to 1 part water
3rd coat:	2 parts SURFHARD to 1 part water

COVERAGERATE

UNDILUTED SURFHARD *	DILUTED
1st coat: 900 ft ² /gal (22.1 m ² /L)	300 ft ² /gal (7.4 m ² /L)
2nd coat: 400 ft ² /gal (9.8 m ² /L)	200 ft ² /gal (4.9 m ² /L)
3rd coat: 225 ft ² /gal (5.5 m ² /L)	150 ft ² /gal (3.7 m ² /L)

***For estimating purposes only**

NOTE: All three coats may not be necessary to harden the floor. If the floor should show patches of white on drying, immediately flood with water and scrub the floor with a mechanical scrubber, rinse and dry. Do not attempt further treatment.

DIRECTIONS FOR USE

Surface Preparation-The surface to be treated should be clean, free of dust, oil, and paint and preferably dry. New concrete surfaces should be at least 7 days old prior to application of SURFHARD. Membrane forming curing compounds should not be used on new concrete if SURFHARD is to be applied.

Extremely soft and porous surfaces should be saturated with water prior to application of hardener. Six hours later, or when the surface is dry, apply the 1st coat of SURFHARD and proceed as indicated previously. This pre-wetting concentrates the chemical at the top level of the concrete rather than at the bottom. The final coat will then harden at the top surface and yield maximum wearing and resistance qualities. In some instances, or in some selected areas, a surface may require an additional application of undiluted SURFHARD to complete hardening and dustproofing.

Mixing-SURFHARD is easily diluted in water with mild agitation.

Placement-Flood each coat of SURFHARD onto the surface and spread with a soft fiber broom, squeegee, or mop. Allow the solution to soak into the concrete for 10-15 minutes and redistribute any puddles that remain. Treated surfaces should be thoroughly dry between coats. Drying time may vary from 4-12 hours depending upon the temperature, humidity, and whether the concrete is indoors or outdoors.

As the various coats of SURFHARD are applied, each succeeding coat will yield increased coverage because the concrete surface is in the process of hardening and becoming more dense. After the third coat the floor should be thoroughly flushed with water and scrubbed with a stiff broom to remove any residual material. If the floor should show patches of white upon drying, immediately flood with water and scrub the floor with a mechanical scrubber, rinse and dry. Do not attempt further treatment.

CLEAN-UP

Clean brushes, tools, equipment and flush sprayer with potable water immediately after use.

PRECAUTIONS/LIMITATIONS

- SURFHARD is not recommended for application to colored concrete surfaces.
- Allow the product to dry 4-6 hours before exposure to traffic.
- SURFHARD is a water-based material and must be kept from freezing.
- If excess SURFHARD is left on the concrete surface, a white residue may form and should be removed by scrubbing immediately.



Surfhard-8.05

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for six (6) months from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.