



Division of Sierra Corporation

BRIGHT GLAZE

Curing and Sealing Compound

Meets Federal EPA's VOC Requirements

Technical Data

1. PRODUCT NAME
BRIGHT GLAZE
Curing and Sealing Compound

2. MANUFACTURER
TK PRODUCTS, DIVISION OF
SIERRA CORPORATION
11400 West 47th Street
Minnetonka, MN 55343
952-938-7223
952-938-8084 (FAX)
e-mail: tksales@tkproduct.com
Website: <http://www.tkproduct.com>

3. PRODUCT DESCRIPTION
BRIGHT GLAZE is a blend of 100% methyl methacrylate polymers used as a specialized superior curing and sealing compound for exposed aggregate. BRIGHT GLAZE is a high viscosity version of Bright Kure & Seal and should be used when a single application glossier than Bright Kure and Seal coating is desired.

BRIGHT GLAZE can be used as a stand alone product or can be applied over BRIGHT KURE & SEAL when a high viscosity and glossier appearance is desired. BRIGHT GLAZE produces a glossier film for curing & sealing the exposed aggregate. BRIGHT GLAZE can be used as a final sealer on architectural concrete, burnish block, terrazzo, brick, paving brick, stone, slate, quarry tile, or any cementitious materials where yellowing or discoloration cannot be allowed. The coating is clear and does not yellow with age or exposure to ultraviolet rays.

BRIGHT GLAZE compared to other curing and sealing compounds provides increased protection from freeze-thaw cycles, deicing salts, chemical erosion and efflorescence; on exposed aggregate it reduces the possibility of aggregate popouts by percolating down in and around the stone to fill gaps and voids. Bright Glaze forms a durable, long lasting film to reduce exposure to water, chemicals, most acids, alkali, oil, grease, fat, food and beverages.

The higher solids content increases the integral strength of the film; increasing abrasion resistance to traffic.

Discoloration from over-use is eliminated. On building and walls, stains from airborne pollutants such as soot, dirt and bird droppings, wash away with water. BRIGHT GLAZE is compatible with most paints and carpet and tile adhesives.

For deep penetration we strongly recommend one coat of BRIGHT KURE & SEAL, then a top coat with BRIGHT GLAZE.

On Exposed Aggregate:
BRIGHT GLAZE intensifies the color, and highlights the exposed aggregate and terrazzo, adding sparkle to the finished project. On burnish block, architectural concrete, brick, stone, slate and quarry tile, the natural colors of the materials are preserved and protected, increasing the aesthetic value and longevity.

On Existing Concrete:
BRIGHT GLAZE penetrates into the slab, binding together the small dusting particles, filling the voids to produce a hard, dust-free, brighter surface, with protection from the elements as well as from exposure to commonplace contaminants. Wear patterns in heavy traffic areas are easily recoated. BRIGHT GLAZE facilitates the removal of grease, oil and rust stains on driveway and garage floors.

Colored Concrete:
BRIGHT GLAZE intensifies the color. The final coat needs to be applied when the colored concrete has cured fully (the concrete should look uniform in color) and dry at the time of application. This eliminates the possibility of moisture becoming trapped between the film and the concrete slab causing a white haze to develop.

On Exposed Aggregate:
Care should be taken to avoid the entrapment of moisture, because in trying to escape, the moisture under the sealer can cause the same white haze to develop. If this happens, roll or spray

TK-00 solvent to dissolve the sealer, the moisture will escape, then the sealer will re-harden clear.

4. TECHNICAL DATA
Composition and Materials:
BRIGHT GLAZE is a blend of 100% methyl methacrylate polymers in a fast drying aromatic solvent. No fillers are used and no oils, waxes or saponifiable resins are contained in the mixture. This product is manufactured with the finest quality raw materials available, close quality control is practiced.

- Non-Volatile Content: 26%
- Flash Point: >100°F
- Moisture Efficiency: .39 kg/m² at 300 sq. ft. per gallon.
- ASTM C-1315 - max. allowed .40 kg/m².
- Drying Time: one hour tack free, two hours open to traffic. Cooler temperatures will require more time.

- Applicable standards:**
- ASTM C-1315-95, Type 1, Class A, B, and C.
 - AASHTO Des. M-148-82
 - Fed. Spec. TT-C-0800
 - ASTM C-309
 - DE CRD - C-300
 - A.I.M. Category: Curing and Sealing Compound, maximum VOC 700g/l.
- A.I.M. Definition** - A liquid membrane-forming compound marketed and sold solely for application to concrete surfaces to reduce the loss of water during the hardening process and to seal old and new concrete providing resistance against alkalis, acids, and ultra violet light, and provide adhesion promotion qualities. The coating meets the requirements of American Society for Testing and Materials (ASTM) C-1315-95, Standard Specification for Liquid Membrane Forming Com-pounds Having Special Properties for Curing and Sealing Concrete.
- Resilient Tile Institute Specification - To be compatible with most resilient tile and carpet adhesives, and most paints. Authorized for use by USDA.



PRODUCTS
3

BRIGHT GLAZE
Curing and Sealing Compound

BRIGHT GLAZE
Curing and Sealing Compound

PRODUCTS
3



5. APPLICATION PROCEDURES AND INSTRUCTIONS

Application:

A test area should be completed to ensure proper adhesion and compatibility. BRIGHT GLAZE is supplied ready for use and requires no mixing or dilution. It is unlawful to further reduce with non-exempt solvents. **New Concrete** allow surface water to completely dissipate. **Existing Concrete** surface must be clean, dry, free from oil, grease, dust, frost and curing compounds (particularly wax base). Large areas can be blown dust free by compressed air, or washed and let dry.

When applying to exposed aggregate as a curing compound the surface should be washed with a mild acid solution to remove the thin film of cement dust, flushed with clean water, and allowed to dry before applying BRIGHT GLAZE. A thin film or 300-500 sq. ft./gal. will do.

BRIGHT GLAZE can be applied with a brush, roller or long nap applicator. Work BRIGHT GLAZE into the concrete avoiding accumulations, runs or sags. On large areas airless sprayer can be used; avoid puddling.

Coverage:

Curing exposed aggregate 300-500 sq./ft per gallon.

Second coat, cured concrete, burnished block 300 to 500 sfpg dependent upon the finish and porosity of the substrate.

Limitations:

Apply in temperatures above 40°F. Follow industry standards for use on colored concrete. Do not use on asphalt or surfaces subject to hydrostatic water pressure or as a waterproofer on below grade surfaces. Sprayers must be equipped with neoprene or other compatible fittings; the solvent can disintegrate rubber fittings. Bright Glaze will not freeze and can be stored outside in cold weather. However, it must be allowed to warm to approximately 50°F before using.

Note 1.

Concrete containing calcium chloride will remain dark longer when sealed. Extenders and additives (concrete admixes, fly ash) are now being added to some ready mixed concrete which can cause inconsistency in the porosity of the concrete. Some areas of the finished concrete may then appear darker than others. To compensate for these variations, coverage ratios should be adjusted.

Equipment Care:

Use TK-00 Solvent. For sprayers, pump the solvent through the spray equipment to remove residue of materials.

Precautions:

BRIGHT GLAZE contains aromatic hydrocarbon. Keep away from heat and flame. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation. Use only with adequate ventilation. Do not breath vapor or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application. Follow respirator manufacturer's direction for respirator use. Any person using a respirator must be trained on proper respirator use. Close container after each use. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. **KEEP OUT OF REACH OF CHILDREN. Interior Use:** Do not allow fumes from this product to penetrate into foodstuffs. Remove animals from quarters until all fumes have dissipated. Turn off all pilot lights. BRIGHT GLAZE in its cured state in non-toxic.

First Aid:

If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If swallowed, do not induce vomiting. Call physician immediately.

In Case of Fire:

Use foam, CO₂, dry chemical. Do not use water spray.

Spills or Leaks:

Eliminate all sources of ignition. If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

For further safety controls, Material Safety Data Sheets are available from TK Distributors, the TK Office and the TK web site. This information should be read before using the product.

6. AVAILABILITY

BRIGHT GLAZE is available through TK Distributors. Contact TK PRODUCTS for the nearest distributor.

Packaged in: 55 gal. drums, 5 gal. pails, and one gallon cans.

Maintenance:

Minimal maintenance is required other than normal sweeping, dusting or mopping. If wear patterns do occur, or spillage removes the coating. TK BRIGHT GLAZE can be reapplied to the affected area.

7. LIMITED WARRANTY

TK Products, warrants that its products conform to their label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of its products by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. **SHOULD ANY OF ITS PRODUCTS FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCTS OR, AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF THE PRODUCTS OF TK PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.** TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing. See TK PRODUCTS DISCLAIMER section below.

8. TECHNICAL SERVICES

The TK office offers assistance with specifications, performance test data and field services.

9. FILING SYSTEMS

Information Handling Services:
PO BOX 1213;
Englewood, CO 80150
Information Marketing Services:
13271 Northend
Oak Park, MI 48237

TK DISCLAIMER

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also LIMITED WARRANTY (Section 7) above.

FOR INDUSTRIAL USE ONLY

2/06