



THE EUCLID CHEMICAL COMPANY

19218 REDWOOD ROAD • Cleveland, OH 44110
(216) 531-9222 • (800) 321-7628 • FAX (216) 531-9596
www.euclidchemical.com

VERTICOAT SUPREME

ONE PART, MODIFIED OVERHEAD REPAIR

VERTICOAT SUPREME is a one component, microsilica and latex modified, nonsag repair mortar. This cement based product is designed for trowel applied vertical and overhead repairs requiring high performance.

PRIMARY APPLICATIONS

- Resurfacing damaged or deteriorated concrete
- Vertical and overhead repairs
- Parking and bridge structures
- Parapet walls
- Marine structures
- Tunnels and dams
- Above and below grade applications

FEATURES/BENEFITS

- One component for easy mixing and handling
- Excellent freeze/thaw resistance for difficult climates
- Low permeability helps protect rebar from corrosion
- High bond strength provides excellent adhesion
- Normal setting times increase workability and reduce waste
- Microsilica and latex modified for high in place performance

PACKAGING/YIELD

VERTICOAT SUPREME is packaged in 50 lb (22.7 kg) moisture resistant bags. Yield is 0.48 ft³ (0.014 m³) per bag when mixed with 2.75 qt (2.6 liter) of water.

COVERAGE

VERTICOAT SUPREME will cover approximately 11.5 ft² (1.1 m²) when placed at an average depth of 1/2" (13 mm). VERTICOAT SUPREME may be placed at thicknesses ranging from 1/4 to 2" (6 mm to 50 mm) per lift.

Shelf Life: 2 years in original, unopened package.

TECHNICAL INFORMATION

Typical Engineering Data

Compressive Strength @ 2.75 qts/50lb/bag

ASTM C 109 modified, 2" (50 mm) cubes

1 day	2,500 psi (17.2 MPa)
3 days	4,000 psi (27.6 MPa)
7 days	5,500 psi (37.9 MPa)
28 days	6,200 psi (42.7 MPa)
56 days	6,700 psi (46.2 MPa)
6 months	7,200 psi (49.6 MPa)

Bond Strength (shear) ASTM C 882 (modified)

Bond Coat

1 day	1,000 psi (6.9 MPa)
3 days	1,500 psi (10.3 MPa)
7 days	1,900 psi (13.1 MPa)
28 days	2,100 psi (14.5 MPa)
56 days	2,700 psi (18.6 MPa)

Direct Tensile Bond Strength

1 day	175 psi (1.2 MPa)
7 days	250 psi (1.7 MPa)
28 days	310 psi (2.1 MPa)

Flexural Strength ASTM C 348

1 day	400 psi (2.8 MPa)
3 days	500 psi (3.4 MPa)
28 days	650 psi (4.5 MPa)
56 days	800 psi (5.5 MPa)

Linear Shrinkage ASTM C-157 50% R. H. @ 73°F (23°C)

3 days	-0.01%
7 days	-0.01%
14 days	-0.02%
28 days	-0.04%
56 days	-0.05%

Sulfate Resistance ASTM C-1012

28 days	+0.005%
56 days	+0.009%

Chloride Permeability ASTM C-1202

7 days	1,000 coulombs
28 days	900 coulombs
56 days	700 coulombs

Freeze/Thaw Resistance, ASTM C-666

Procedure A @ 500 cycles Relative Durability Modulus-100%

Working Time: 30 minutes

Set Times 70°F (21°C) ASTM C-266

Initial Set: 1 hour

Final Set: 2 1/2 hours

Unit Weight: 115 lb/ft³ (1836 kg/m³)

Appearance

VERTICOAT SUPREME is a free flowing powder designed to be mixed with water. After mixing and placing, the color may initially appear darker than the surrounding concrete. While this color will lighten up substantially as the VERTICOAT SUPREME cures and dries out, the repair may always appear somewhat darker than the surrounding concrete.

The final finish can be any texture consistent with that expected from concrete and should match the surrounding concrete.

DIRECTIONS FOR USE

Surface Preparation-The concrete must be clean and rough. All oil, dirt, debris, paint and unsound concrete must be removed. The surface must be prepared mechanically using a bushhammer, sandblaster or jackhammer which will give a surface profile of a minimum 1/8" (3 mm) and expose the coarse aggregate of the concrete. The final step in cleaning should be the complete removal of all residue with a vacuum cleaner or pressure washing. **The concrete surface must be dampened prior to application of the bond coat.**

Exposed Reinforcement Steel-Exposed rebar may be treated with an anti-corrosion coating such as CORR-BOND or EUCO #452 LV epoxy. Remove all loose rust and scaling, preferably by sandblasting to white metal prior to coating the rebar.

Bonding-After the surface has been prepared and predampened, all areas must be primed with CORR-BOND or with a bond coat of VERTICOAT SUPREME. Produce a bond coat of this product by mixing the material as indicated below and then add an additional 1 to 1.5 pint (0.5-0.75 liter) of water to the mix. Brush the bond coat on to the prepared and predampened concrete. Apply VERTICOAT SUPREME before the bond coat has dried.

Mixing-Product is normally mixed with a drill and "jiffy" type mixer. Use a paddle type mortar mixer for large placements. All materials should be in the proper temperature range of 60°F (16°C) - 90°F (32°C). Note: Do not mix more material than can be placed within 20 minutes.

Add the appropriate amount of water for the batch size [2.5-3.0 qt (2.4-2.8 liter)/bag] and then add the dry product. Mix 3-5 minutes. The mixed product should be quickly transported to the repair area and placed immediately.

Placement- Product should be placed in lifts 1/4 to 2" (6 to 50 mm) thickness. Trowel into place and allow to stiffen before the next lift. If additional lifts will be placed after the product has hardened, cross hatch the surface of the previous lift to provide for a secure bond for the next lift.

Finishing-Finish the repair material to the desired texture and/or to match the surrounding concrete. Do not add additional water to the surface during the finishing operation. If additional liquid is required, use EUCOBAR finishing aid.

Curing & Sealing-Proper curing procedures are important to ensure the durability and quality of the repair. To prevent drying surface cracking, cure VERTICOAT SUPREME with a high solids curing compound, such as SUPER AQUA-CURE VOX or SUPER DIAMOND CLEAR VOX. Note: Do not use a solvent based curing compound on this product. In hot, windy or direct sunlight situations, apply a second coat of curing compound after the initial coat is dry.

If a curing compound is not desired, cover with polyethylene sheeting for a minimum of three (3) days.

CLEAN-UP

Clean tools and equipment with water before the material hardens.

PRECAUTIONS / LIMITATIONS

- Do not allow repairs to freeze until the material has reached a minimum of 1000 psi (7 MPa) compressive strength [approximately 3 days at 40°F (4°C)].
- In adverse temperatures, follow ACI recommendations for hot/cold weather concreting practices.
- Use only potable water for mixing.
- Minimum application thickness 1/4" (6 mm).
- Minimum surface and ambient temperature 45°F (7°C) and rising at time of application.
- For optimum results, condition material to 65-85°F (18-29°C).
- Store product in a dry place.



Verticoat Supreme-8.04

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for six (6) months from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.